JOTO
Bringing images to life!™

PAROPY™
image trans

PAROPY CL WATER SLIDE WHITE (FOR DARKS)

APPLICATION INSTRUCTIONS

NOTES

Recommended Materials
White or Light Colored
Candles
Glass
Metal
Wood
Soap

Accessories Required
Computer, Color Laser Printer, Large Water bowl, Dish Soap.

Printable side
The printable side is the white glossy coated side.

Storage
Paropy CL Water Slide has an indefinite shelf life when stored at room temperature. Keep away from direct heat, sunlight, and humidity.

Tips
For extra durability on candles, we suggest using a glue stick to help adhere the WT transfer paper.

The candle can also be heated with a blow dryer to soften the wax before applying the transfer.

STEP BY STEP

Paropy CL Water Slide will allow image transfer to objects that cannot be heated with a heat press.

This paper will work in most Oil and Non-Oil Laser Copiers and Printers. It is recommended that you do a test before commercial application.

Step 1
Feed transfer paper into laser printer so that the printer is printing on the printable side (white glossy coated side). It is recommended to use the bypass tray when printing.

Step 2
Design your image and resize if necessary. Print the design right reading.

Step 3
Trim your image. It is recommended to use a cutter/plotter to trim accurately. Any untrimmed, unimaged areas will turn white when transferred. Use 25mm offset, at around 60gf, 5-10cm/s speed.

Step 4
Fill good-sized bowl with water and add about 5-10% liquid dish soap.

Step 5
Then place the imaged paper in bowl for 3-4 minutes.

Step 6
Gently remove the film from the paper backing. If possible this step should be done while the paper is in the water bowl.

Step 7
Lay imaged film onto substrate with the image face up. With a sponge and finger, gently position correctly the image and iron out any air bubbles.

Step 8
Let the transfer and material dry for at least 6-8 hour before handling.

Step 9 (optional)
To improve scratch resistance, the imaged substrate can be heated at 266°F- 302°F (130°C-150°C) for approximately 30 minutes. This step can be done only on heat resistant objects.